TECHNICAL DATA

Sentinel Canada

SL 123 K

TYPICAL SPECIFICATIONS:

NLGI Consistency Number	1 1/2
Thickener	Lithium Complex
Texture	Smooth, Tacky
Color	Red
Worked 60 Penetration, D-217	285-315
Dropping Point, D-2265, ^{o}F (^{o}C)	500 (260) min.
Wheel Bearing Leakage, D-1263, g loss	2
Water Washout, D-1264, % loss	6.0 at 175°F
Rust Prevention, D-1743, rating	Pass
Copper Corrosion, D-4048, rating	Pass
Oxidation Stability, D-942, psi drop	5 at 100 hours
Oil Separation, D-1742, % loss	3
Timken OK Load, D-2509, lb	60 min.
Four-Ball Wear, D-2266, mm	0.50
Four-Ball EP Weld Point, D-2596, kgf	315
Four-Ball Load Wear Index, D-2596, kgf	45
Approximate Temperature Range, ^{o}F (^{o}C)	-10 to 325 (-23 to 163)

PROPERTIES OF OIL PLUS OIL SOLUBLE ADDITIVES:

Viscosity at 100°C, cSt	45.09
Viscosity at 40°C, cSt	635.6
Viscosity Index	115 min.
Pour Point, ^{o}F (^{o}C)	+5 (-15) max.
Flash Point, ^{o}F (^{o}C)	425 (218) min.

FEATURES:

- Premium quality lithium complex multi-purpose grease.
- Fully additive treated: EP/antiwear, rust and oxidation inhibited.
- Water insoluble and water washout resistant.
- An exceptionally versatile multi-purpose grease.
- Superior wheel bearing and frame performance.
- Superior protection to lubricate a wide variety of severe duty automotive trucking, industrial, mining and construction equipment.

Rev. November 2016

Sentinel Canada
7300 St-Jacques, Montreal, Quebec, Canada H4B 1W1
Tel.: 514-483-6500 / 1-800-361-2517 Fax: 514-483-3284 E-mail: sentinel@sentinelcanada.com

The information contained herein is to the best of our knowledge, true and exact, but all recommendations are made without guaranty because the conditions of their use is beyond the control of Sentinel Canada. We deny any responsibility resulting from the use of these products.